


Hobart® 718MC



AWS E7018 H4R/E7018-1 H4R (E4818*)

WELDING POSITIONS:



FEATURES:

- Low moisture absorption
- Easy slag removal
- Low spatter in all positions
- Good wetting action
- Reliable starts and restarts
- Very stable arc

BENEFITS:

- Reduces worry of moisture pick-up and hydrogen cracking
- Eliminates going back to oven for "fresh" electrodes
- Reduces clean-up time
- Results in excellent weld bead appearance
- Enhances bead contour
- Provides better welds due to no porosity
- Easy to control

APPLICATIONS:

- Offshore rigs
- Steel structures
- Weldments
- Railroad
- Shipbuilding
- Petrochemical plants
- Free machining steels
- Boiler code applications
- Power plates
- Low alloy structures
- Field erections
- Enameling steels
- Low, medium, high carbon steels

TYPE OF CURRENT: Direct Current Electrode Positive (DCEP) or AC

ARC LENGTH: Very short arc (less than half the diameter of the electrode)

FLAT: Angle electrode 10-15° from 90°

VERTICAL-UP: Use weaving technique, but do not use oscillation or whipping motion

VERTICAL-DOWN: Not recommended

OVERHEAD: Use slight weaving motion within the puddle

STORAGE: 250° to 350°F (to ensure a low hydrogen weld deposit, storage in an oven is recommended)

RECONDITIONING: If exposed to the atmosphere for extended periods, the electrode should be reconditioned at 500° to 800°F for one to two hours

TYPICAL WELD METAL CHEMISTRY* (CHEM PAD):

Weld Metal Analysis (%)		AWS Spec (max)
Carbon (C)	0.04	0.15
Manganese (Mn)	1.10	1.60
Silicon (Si)	0.45	0.75
Phosphorus (P)	0.011	0.035
Sulphur (S)	0.015	0.035
Nickel (Ni)	0.06	0.30
Chromium (Cr)	0.05	0.20
Molybdenum (Mo)	<0.01	0.30
Vanadium (V)	<0.01	0.08
Mn + Ni + Cr + Mo	1.22	1.75

Note: AWS specification single values are maximums.

TYPICAL MECHANICAL PROPERTIES* (As Welded):

Mechanical Tests		AWS Spec (min)
Tensile Strength	85,000 psi (550 MPa)	70,000 psi (483 MPa)
Yield Strength	73,000 psi (478 MPa)	58,000 psi (400 MPa)
Elongation % in 2" (50 mm)	27%	22%
Reduction of Area	70%	Not required

TYPICAL CHARPY V-NOTCH IMPACT VALUES* (As Welded):

		AWS Spec (min)
Avg. @-20°F (-29°C)	123 ft•lbs (167 Joules)	20 ft•lbs (27 Joules)
Avg. @-50°F (-45°C)	106 ft•lbs (144 Joules)	20 ft•lbs (27 Joules)

TYPICAL DIFFUSIBLE HYDROGEN:

Hydrogen Equipment		AWS Spec
(GAS CHROMATOGRAPHY)	1.4 ml/100g	4.0 ml/100g

TYPICAL CTOD VALUES (Tested @ +14°F):

0.969 mm (.0381")
0.294 mm (.0116")
0.491 mm (.0193")

*The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and Hobart Brothers LLC expressly disclaims any liability incurred from any reliance thereon. Typical data are those obtained when welded and tested in accordance with the AWS A5.1 specification. Other tests and procedures may produce different results. No data is to be construed as a recommendation for any welding condition or technique not controlled by Hobart Brothers LLC.

Hobart® 718MC

Diameter Inches	(mm)	Type of Current	Minimum Amps	Optimum Amps	Maximum Amps
3/32	(2.4)	DCEP or AC	70	90	110
1/8	(3.2)	DCEP or AC	90	140	165
5/32	(4.0)	DCEP or AC	125	180	220

*For out-of-position welding, reduce amperage shown by 15%.

Diameter Inches	(mm)	Type of Current	Amps	Volts	Deposition Rate lbs/hr	(kg/hr)	Deposition Efficiency %
3/32	(2.4)	DCEP or AC	90	22.0	1.90	(0.9)	62.7
1/8	(3.2)	DCEP or AC	140	26.5	2.89	(1.3)	73.1
5/32	(4.0)	DCEP or AC	180	28.0	3.82	(1.7)	62.5

- Maintaining a proper welding procedure - including pre-heat and interpass temperatures - may be critical depending on the type and thickness of steel being welded.

STANDARD DIAMETERS AND PACKAGES: For a complete list of diameters and packaging, please contact Hobart Brothers at (800) 424-1543 or (937) 332-5188 for International Customer Service.

Diameter Inches	(mm)	Length Inches	(mm)	10-lb. (4.5kg) Plastic Pak	50-lb. (22.7kg) Can	MIL Tested	
Net Pallet Weight				2100-lb. (945kg)	*3000-lb. (1362kg)	10-lb. (4.5kg) Can	50-lb. (22.7kg) Can
3/32	(2.4)	14	(355)	S115932-089	S115932-035	S115932M-033	S115932M-035
1/8	(3.2)	14	(355)	S115944-089	S115944-035	S115944M-033	S115944M-035
5/32	(4.0)	14	(355)	S115951-089	S115951-035	—	—

CONFORMANCES AND APPROVALS:

- AWS A5.1, E7018 H4R/E7018-1 H4R
- ASME SFA 5.1, F-4, A-1 E7018
- ABS, 3Y H5
- MIL-DTL-22200/1H, MIL-7018-M (3/32" and 1/8" diameters)

TECHNICAL QUESTIONS? For technical support of Hobart Filler Metals products, contact the Applications Engineering department by phone toll-free at 1-800-532-2618 or by e-mail at Applications.Engineering@hobartbrothers.com

CAUTION:

Consumers should be thoroughly familiar with the safety precautions on the warning label posted in each shipment and in the American National Standard Z49.1, "Safety in Welding and Cutting," published by the American Welding Society, 8669 NW 36th St., Miami, FL 33166 (can also be downloaded online at www.aws.org); OSHA Safety and Health Standards 29 CFR 1910 is available from the U.S. Department of Labor, Washington, D.C. 20210

Safety Data Sheets on any Hobart Brothers LLC product may be obtained from Hobart Customer Service or at www.hobartbrothers.com.

Because Hobart Brothers LLC is constantly improving products, Hobart reserves the right to change design and/or specifications without notice.

Hobart is a registered trademark of Hobart Brothers LLC, Troy, Ohio.

Revision Date: 240328 (Replaces 210513)
612-N, INDEX

